

weber.dress H

Ready thin render

■ Description

Cement based, hand applicable thin render.

■ Advantages

- Prevents efficiency and quality loss due to dosing.
- Labor and time savings.
- Suitable substrate preparation for final layer coating.

■ Range of application

- Applied as thin render in interior and exterior of all buildings.

■ Application substrates

- Interior and exterior;
 - Cement based traditional rough render or **weber.dress L**.
- Please consult us for all other application substrates.

■ Application properties

- Mixing time: 5 minutes
- Aging life: 15 minutes.
- Pot life: 2 hours
- Time to wait between layers: 3-6 hours
- Time to wait for final layer application on **weber.dress H**: 7 days
- Time for finishing: 2 hours.
- Application thickness: 1-3 mm.
- Layer thickness: max. 2 mm.

■ Conditions of application

- The surface and ambient temperature is between: +5 °C and +30 °C.
- Avoid application under strong wind or sun.
- It should not be used on substrates which are frozen or melting or have the risk of frost within 24 hours.

■ Preparation of substrates

- The substrate should be clean, sound and damp.
- Cracks and defects deeper than 3 mm should be repaired with **weber.rep MA 200** or **weber.rep HKS** 24 hours before the application.
- The substrate should be damped before the application, and saturated with water under very hot and windy weather.

■ Application

- Average 7 lt. clean water should be added to 25 kg **weber.dress H**.
- **weber.dress H** should be mixed with trowel or low-speed hand mixer until homogenous state is achieved. The mortar should be aged for 15 minutes before the application.
- **weber.dress H** should be applied on the substrate in equal thickness via steel trowel. The first layer should not be thinner than 1 mm. If more than one layer is applied, wait for 3-6 hours between layers and total thickness should not exceed 3 mm.
- Smoothness of substrate should be ensured with finishing trowel. The substrate will be ready for paint and wall paper coating after the application.

■ Attention points

- Aging time should be observed after mixing **weber.dress H** with water and mortar should be mixed well again just before the application.
- The substrate should be damped for 2-3 days after the application.
- No foreign materials should be added in the mortar (cement, lime, plaster, etc).

■ Limits of application

- Not applicable on gas concrete.
- Not applicable on unstable substrates and substrates with render deterioration thicker than 3 mm.
- Not applicable on substrates painted, with ready colored render, spread rendered and external coating.
- Not applicable on plaster substrate.

■ Consumption

1,5 kg/m²
(for 1 mm layer thickness).

■ Packaging

Net 25 kg bags
(64 units in pallet, 1600 kg).

■ Pallet size

107 x 107 cm.

■ **Color**

Grey.

■ **Application tools**

Hand mixer, steel trowel, finishing trowel.

■ **Shelf life**

1 year as of the production date in dry and moisture-free environment provided that packages will not be opened. Package should be kept tightly closed when not in use.

FOR INFO

> The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.

> **Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş.** is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.



Saint-Gobain Weber
Yapı Kimyasalları San. ve Tic. A.Ş.
Ankara Karayolu 26. Km.
35171 Kemalpaşa • İzmir • Türkiye

Tel : +90 (232) 397 07 00
Fax : +90 (232) 397 08 00
www.weber.com.tr
info@weber.com.tr



Weber products are
produced at ISO 9001:2008
Quality Management
System Certified
production facilities.

